

PAPIERY POWLEKANE

Dane techniczne

	Gramatura	Grubość	Masa	Gładkość	Chropowatość	Biel	Jasność	Nieprzezroczystość	Połysk
Jednostka	g/m ²	µm	cm ³ /g	sec	µm	%	%	%	%
78	78 ± 4%	69 ± 5	0.88	500 ↑	1.7 ± 0.3	115 ± 10	92 ± 2	90 ± 2	30 ± 3
80	80 ± 4%	71 ± 5	0.89	500 ↑	1.7 ± 0.3	115 ± 10	92 ± 2	90 ± 2	30 ± 3
85	85 ± 4%	75 ± 5	0.88	500 ↑	1.7 ± 0.3	115 ± 10	92 ± 2	91 ± 2	30 ± 3
89	89 ± 4%	80 ± 5	0.90	500 ↑	1.7 ± 0.3	115 ± 10	92 ± 2	92 ± 2	30 ± 3
90	90 ± 4%	81 ± 5	0.90	500 ↑	1.7 ± 0.3	115 ± 10	92 ± 2	92 ± 2	30 ± 3
95	95 ± 4%	85 ± 5	0.89	500 ↑	1.7 ± 0.3	115 ± 10	92 ± 2	93 ± 2	30 ± 3
100	100 ± 4%	91 ± 5	0.91	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	93 ± 2	30 ± 3
104	104 ± 4%	95 ± 5	0.91	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	94 ± 2	30 ± 3
105	105 ± 4%	96 ± 5	0.91	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	94 ± 2	30 ± 3
110	110 ± 4%	101 ± 5	0.92	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	95 ± 2	30 ± 3
113	113 ± 4%	103 ± 5	0.91	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	95 ± 2	30 ± 3
115	115 ± 4%	105 ± 5	0.91	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	96 ± 2	30 ± 3
118	118 ± 4%	107 ± 5	0.91	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	96 ± 2	30 ± 3
120	120 ± 4%	108 ± 5	0.90	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	96 ± 2	30 ± 3
125	125 ± 4%	114 ± 5	0.91	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	97 ± 2	30 ± 3
128	128 ± 4%	116 ± 5	0.91	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	97 ± 2	30 ± 3
130	130 ± 4%	118 ± 5	0.91	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	97 ± 2	30 ± 3
135	135 ± 4%	125 ± 5	0.93	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	97 ± 2	30 ± 3
137	137 ± 4%	127 ± 5	0.93	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	97 ± 2	30 ± 3
140	140 ± 4%	130 ± 5	0.93	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	97 ± 2	30 ± 3
148	148 ± 4%	139 ± 5	0.94	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	98 ± 2	30 ± 3
150	150 ± 4%	140 ± 5	0.93	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	98 ± 2	30 ± 3
157	157 ± 4%	150 ± 5	0.96	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	98 ± 2	30 ± 3
170	170 ± 4%	165 ± 5	0.97	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	98 ± 2	30 ± 3
180	180 ± 4%	176 ± 5	0.98	500 ↑	2.0 ± 0.3	115 ± 10	92 ± 2	98 ± 2	30 ± 3
200	200 ± 4%	200 ± 5	1.00	300 ↑	2.0 ± 0.3	116 ± 5	91 ± 2	98 ± 2	30 ± 3
250	250 ± 4%	260 ± 10	1.04	300 ↑	2.5 ± 0.3	116 ± 5	91 ± 2	99 ± 2	30 ± 3
300	300 ± 4%	320 ± 10	1.06	300 ↑	2.7 ± 0.3	116 ± 5	91 ± 2	99 ± 2	30 ± 3
350	350 ± 4%	380 ± 10	1.08	300 ↑	2.7 ± 0.3	116 ± 5	91 ± 2	99 ± 2	30 ± 3