

# PAPIERY POWLEKANE

## Dane techniczne

	Gramatura	Grubość	Masa	Gładkość	Chropowatość	Połysk	Biel	Jasność	Nieprzezroczystość
Jednostka	g/m <sup>2</sup>	µm	cm <sup>3</sup> /g	sec	µm	%	%	%	%
78	78 ± 4%	63 ± 3	0.81	3.500 ↑	0.8 ± 0.3	73 ± 3	120 ± 10	92 ± 2	90 ± 2
80	80 ± 4%	64 ± 3	0.80	3.500 ↑	0.8 ± 0.3	73 ± 3	120 ± 10	92 ± 2	90 ± 2
85	85 ± 4%	66 ± 3	0.78	3.500 ↑	0.8 ± 0.3	73 ± 3	120 ± 10	92 ± 2	91 ± 2
89	89 ± 4%	69 ± 3	0.78	5.000 ↑	0.8 ± 0.3	75 ± 3	120 ± 10	92 ± 2	92 ± 2
90	90 ± 4%	70 ± 3	0.78	5.000 ↑	0.8 ± 0.3	75 ± 3	120 ± 10	92 ± 2	92 ± 2
95	95 ± 4%	74 ± 3	0.78	5.000 ↑	0.8 ± 0.3	75 ± 3	120 ± 10	92 ± 2	93 ± 2
100	100 ± 4%	80 ± 3	0.80	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	93 ± 2
104	104 ± 4%	82 ± 3	0.79	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	94 ± 2
105	105 ± 4%	83 ± 3	0.79	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	94 ± 2
110	110 ± 4%	88 ± 3	0.80	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	95 ± 2
113	113 ± 4%	90 ± 3	0.80	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	95 ± 2
115	115 ± 4%	92 ± 3	0.80	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	95 ± 2
118	118 ± 4%	94 ± 3	0.80	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	95 ± 2
120	120 ± 4%	96 ± 3	0.80	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	95 ± 2
125	125 ± 4%	101 ± 3	0.81	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	96 ± 2
128	128 ± 4%	102 ± 3	0.80	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	96 ± 2
130	130 ± 4%	103 ± 3	0.79	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	96 ± 2
135	135 ± 4%	113 ± 3	0.84	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	97 ± 2
137	137 ± 4%	114 ± 3	0.83	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	97 ± 2
140	140 ± 4%	115 ± 3	0.82	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	97 ± 2
145	145 ± 4%	121 ± 3	0.83	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	97 ± 2
148	148 ± 4%	123 ± 3	0.83	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	97 ± 2
150	150 ± 4%	125 ± 3	0.83	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	97 ± 2
157	157 ± 4%	129 ± 3	0.82	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	97 ± 2
160	160 ± 4%	131 ± 3	0.82	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	97 ± 2
170	170 ± 4%	143 ± 3	0.84	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	98 ± 2
180	180 ± 4%	152 ± 3	0.84	3.000 ↑	0.8 ± 0.3	70 ± 3	120 ± 10	92 ± 2	98 ± 2
200	200 ± 4%	178 ± 3	0.89	3.000 ↑	0.9 ± 0.3	72 ± 3	120 ± 5	91 ± 2	98 ± 2
250	250 ± 4%	235 ± 3	0.94	2.000 ↑	1.2 ± 0.3	72 ± 3	120 ± 5	91 ± 2	99 ± 2
300	300 ± 4%	290 ± 3	0.96	1.700 ↑	1.2 ± 0.3	70 ± 3	120 ± 5	91 ± 2	99 ± 2
350	350 ± 4%	342 ± 3	0.87	1.700 ↑	1.2 ± 0.3	70 ± 3	120 ± 5	91 ± 2	99 ± 2